

Désignation	Norme EN (EUROPE)	FRANCE	USA	GB	ALLEMAGNE	
ISO	Numérique	NFA	UNS	BS	DIN	Werkstoff

Laitons						
CuZn35Pb1	CW600N	-	C34000	CZ118	-	-
CuZn35Pb2	CW601N	CuZn35Pb2	C34200	CZ119	-	-
CuZn36Pb2As	CW602N	-	-	CZ132	-	-
CuZn36Pb3	CW603N	CuZn36Pb3	C36000	CZ124	CuZn36Pb3	2.0375
CuZn37Pb0,5	CW604N	-	C33500	-	-	-
CuZn37Pb1	CW605N	-	C35000	-	-	-
CuZn37Pb2	CW606N	-	C35300	CZ121/119	-	-
CuZn38Pb1	CW607N	-	C35000	-	-	-
CuZn38Pb2	CW608N	-	C37700	CZ128	-	-
CuZn38Pb4	CW609N	-	-	CZ121-Pb4	-	-
CuZn39Pb0,5	CW610N	-	C36500	CZ123/137	-	-
CuZn39Pb1	CW611N	-	C37100	CZ129	-	-
CuZn39Pb2	CW612N	CuZn39Pb2	C37700	CZ12	-	-
CuZn39Pb2Sn	CW613N	-	C48500	-	-	-
CuZn39Pb3	CW614N	-	C38500	CZ121-Pb3	CuZn39Pb3	2.0401
CuZn39Pb3Sn	CW615N	-	-	-	-	-
CuZn40Pb1Al	CW616N	-	-	-	-	-
CuZn40Pb2	CW617N	-	C38010	CZ122	CuZn40Pb2	2.0402
CuZn40Pb3	-	CuZn40Pb3	-	-	-	-
CuZn40Pb2Al	CW618N	-	C38000	-	-	-
CuZn40Pb2Sn	CW619N	-	-	-	-	-
CuZn41Pb1Al	CW620N	-	-	-	-	-
CuZn42PbAl	CW621N	-	-	-	-	-
CuZn43Pb1Al	CW622N	-	C38000	-	-	-
CuZn43Pb2	CW623N	-	-	CZ130	-	-
CuZn43Pb2Al	CW624N	-	-	CZ130	-	-

Désignation	Norme EN (EUROPE)	FRANCE	USA	GB	ALLEMAGNE	
ISO	Numérique	NFA	UNS	BS	DIN	Werkstoff
Cuivres purs						
Cu-ETP1	CW003A	-	-	C100	-	-
Cu-ETP	CW004A	Cu-a1	C11000	C101	E-Cu57/58	2.0060/65
Cu-FRHC	CW005A	Cu-a2	C11020	C102	-	-
Cu-FRTP	CW006A	Cu-a3	C12500	C104	-	-
Cu-OF1	CW007A	-	-	-	-	-
Cu-OF	CW008A	Cu-c1	C10200	C103	OF-Cu	2.0040
Cu-OFE (OFHC)	CW009A	Cu-c2	C10100	C110	OF-Cu	2.0040
Cu-Ag0,04	CW011A	-	-	-	-	-
Cu-Ag0,07	CW012A	-	-	-	-	-
CuAg0,10	CW013A	-	-	-	-	-
CuAg0,04P	CW014A	-	-	-	-	-
CuAg0,07P	CW015A	-	-	-	-	-
CuAg0,10P	CW016A	-	-	-	-	-
CuAg0,04(OF)	CW017A	-	C14415	-	-	-
CuAg0,07(OF)	CW018A	-	-	-	-	-
CuAg0,10(OF)	CW019A	-	-	-	-	-
Cu-PHC	CW020A	-	C10300	-	SE-Cu	2.0070
Cu-HCP	CW021A	-	C10300	-	SE-Cu	2.0070
Cu-PHCE	CW022A	-	-	-	-	-
Cu-DLP	CW023A	Cu-b2	C12000	-	SW-Cu	2.0076
Cu-DHP	CW024A	Cu-b1	C12200	C106	SF-Cu	2.0090

Désignation	Norme EN (EUROPE)	FRANCE	USA	GB	ALLEMAGNE	
ISO	Numérique	NFA	UNS	BS	DIN	Werkstoff

Cuivres faiblement alliés						
CuBe1,7	CW100C	CuBe1,7	C17000	CB101	CuBe1,7	2.1245
CuBe1,9	-	CuBe1,9	C17200	-	-	-
CuBe2	CW101C	-	C17200	-	CuBe2	2.1247
CuBe2Pb	CW102C	-	C17300	-	CuBe2Pb	2.1248
CuCo1Ni1be	CW103C	-	-	-	-	-
CuCo2Be	CW104C	-	C17500	C112	CuCo2Be	2.1285
CuCr1	CW105C	-	C18200	CC101	-	-
CuCr1Zr	CW106C	-	-	CC102	-	-
CuFe2P	CW107C	-	-	-	-	-
CuNi1P	CW108C	-	-	C113	-	-
CuNi1Si	CW109C	-	C19101	-	-	-
CuNi2Be	CW110C	-	C17510	-	CuNi2Be	2.0850
CuNi2Si	CW111C	-	C70250	-	CuNi2Si	2.0855
CuNi3Si1	CW112C	-	-	-	CuNi3Si	2.0857
CuPb1P	CW113C	-	C18700	-	CuPb1P	2.116
CuSp	CW114C	-	C14700	C111	CuSp	2.1498
CuSi1	CW115C	-	C65100	-	-	-
CuSi3Mn1	CW116C	-	C65500	CS101	CuSi3Mn	2.1525
CuSn0,15	CW117C	-	C14415	-	-	-
CuTep	CW118C	-	C14500	C109	CuTep	2.1546
CuZn0,5	CW119C	-	-	-	-	-
CuZr	CW120C	-	C15000	-	CuZr	2.158

Désignation	Norme EN (EUROPE)	FRANCE	USA	GB	ALLEMAGNE	
ISO	Numérique	NFA	UNS	BS	DIN	Werkstoff

Alliages cuivre complexes						
CuZn13Al1Ni1Si1	CW700R	-	-	-	-	-
CuZn19Sn	CW701R	-	C43500	-	-	-
CuZn20Al2As	CW702R	-	-	CZ110	CuZn20Al2	2.0460
CuZn23Al3Co	CW703R	-	-	-	-	-
CuZn23Al6Mn4Fe3Pb	CW704R	-	-	-	-	-
CuZn25Al5Fe2Mn2Pb	CW705R	-	C67000	CZ116	-	-
CuZn28Sn1As	CW706R	-	-	CZ111	CuZn28Sn1	2.0470
CuZn30As	CW707R	-	-	CZ126/105	-	-
CuZn31Si1	CW708R	-	-	-	CuZn31Si1	2.0490
CuZn32Pb2AsFeSi	CW709R	-	-	-	-	-
CuZn35Ni3Mn2AlPb	CW710R	-	-	-	CuZn35Ni2	2.0540
CuZn36Pb2Sn1	CW711R	-	C48400	CZ134	-	-
CuZn36Sn1Pb	CW712R	-	C48200	CZ112	-	-
CuZn37Mn3Al2PbSi	CW713R	-	C67420	CZ135	-	-
CuZn37Pb1Sn1	CW714R	-	C48200	-	-	-
CuZn38AlFeNiPbSn	CW715R	-	-	-	-	-
CuZn38Mn1Al	CW716R	-	-	-	CuZn37Al1	2.0510
CuZn38Sn1As	CW717R	-	-	-	-	-
CuZn39Mn1AlPbSi	CW718R	-	-	-	-	-
CuZn39Sn1	CW719R	-	C46400	CZ133	CuZn38Sn1	2.0530
CuZn40Mn1Pb1	CW720R	-	-	CZ136	CuZn40Mn1Pb	2.0580
CuZn40Mn1Pb1AlFeSn	CW721R	-	-	CZ114	-	-
CuZn40Mn1Pb1FeSn	CW722R	-	-	CZ115	-	-
CuZn40Mn2Fe1	CW723R	-	-	-	-	-